

# Sound absorption values – Ceilings

Constructions with Trolldtekt panels

Tested according to DS/ISO 354

TCH = Total Construction Height

## Contents

### Trolldtekt installed on concrete

Trolldtekt acoustic panels	2
Trolldtekt Plus	5
Trolldtekt design & Trolldtekt design Plus	7
Trolldtekt A2	7





### Trolldtekt installed as suspended ceiling

Trolldtekt acoustic panels	8
Trolldtekt Plus	12
Trolldtekt design & Trolldtekt design Plus	14
Trolldtekt A2 & Trolldtekt A2 Plus	15





Trolldtekt baffles	16
--------------------	----



# Troldekt acoustic panels

## Installed on concrete

Constructions with Troldekt and mineral wool installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 95 mm mineral wool 30 kg/m<sup>3</sup> 25 mm Troldekt TCH 120 mm</p>	Fine structure	0.55	1.00	1.00	0.90	0.80	1.00	0.90	1.00	A	April 2017	SRL
	Ultrafine structure	0.55	1.00	1.00	0.95	0.90	1.00	0.95	1.05	A	April 2017	SRL
	Extreme fine structure	0.55	1.00	1.00	0.95	0.90	1.00	0.95	1.00	A	April 2017	SRL
 <p>Concrete 95 mm mineral wool 30 kg/m<sup>3</sup> 35 mm Troldekt TCH 130 mm</p>	Fine structure*	0.60	1.00	1.00	0.85	0.95	0.95	0.95	0.95	A	2015	Peutz
	Ultrafine structure	0.65	1.00	1.00	0.95	1.00	1.00	1.00	1.05	A	June 2018	SRL
	Extreme fine structure	0.60	1.00	1.00	0.95	1.00	1.00	1.00	1.05	A	June 2017	SRL
 <p>Concrete 45 mm mineral wool 30 kg/m<sup>3</sup> 25 mm Troldekt TCH 70 mm</p>	Fine structure	0.25	0.85	1.00	0.90	0.95	1.00	0.90	0.95	A	April 2017	SRL
	Ultrafine structure	0.25	0.75	1.00	1.00	0.90	1.00	0.95	0.95	A	April 2017	SRL
	Extreme fine structure	0.25	0.80	1.00	0.95	0.85	1.00	0.95	0.95	A	April 2017	SRL
 <p>Concrete 45 mm mineral wool 30 kg/m<sup>3</sup> 35 mm Troldekt TCH 80 mm</p>	Fine structure	0.30	0.85	1.00	0.85	0.90	1.00	0.90	0.95	A	June 2017	SRL
	Ultrafine structure	0.30	0.85	1.00	0.95	0.90	1.00	0.95	1.00	A	June 2017	SRL
	Extreme fine structure	0.30	0.85	1.00	0.95	0.95	1.00	1.00	0.95	A	June 2017	SRL




\*95 mm mineral wool 33 kg/m<sup>3</sup>


Constructions with Troldekt and mineral wool installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 30 mm mineral wool 70 kg/m<sup>3</sup> 25 mm Troldekt TCH 55 mm</p>	Fine structure	0.20	0.70	1.00	1.00	0.85	1.00	0.90	0.95	A	April 2017	SRL
	Ultrafine structure	0.20	0.65	1.00	1.00	1.00	1.00	0.95	0.95	A	April 2017	SRL
	Extreme fine structure	0.20	0.65	1.00	1.00	0.90	1.00	0.90	0.95	A	April 2017	SRL
 <p>Concrete 50 mm mineral wool 90 kg/m<sup>3</sup> 25 mm Troldekt TCH 75 mm</p>	Fine structure	0.35	1.00	1.00	1.00	0.95	1.00	1.00	1.10	A	April 2017	SRL
	Ultrafine structure	0.35	1.00	1.00	1.00	1.00	1.00	1.00	1.10	A	April 2017	SRL
	Extreme fine structure	0.35	1.00	1.00	1.00	0.95	1.00	1.00	1.10	A	April 2017	SRL
 <p>Concrete 30 mm mineral wool 70 kg/m<sup>3</sup> 35 mm Troldekt TCH 65 mm</p>	Fine structure	0.20	0.70	1.00	1.00	0.90	1.00	0.95	0.95	A	June 2017	SRL
	Ultrafine structure	0.25	0.75	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
	Extreme fine structure	0.25	0.75	1.00	1.00	0.90	1.00	0.95	1.00	A	June 2017	SRL
 <p>Concrete 50 mm mineral wool 90 kg/m<sup>3</sup> 35 mm Troldekt TCH 85 mm</p>	Fine structure	0.40	1.00	1.00	0.95	0.95	1.00	1.00	1.05	A	June 2017	SRL
	Ultrafine structure	0.40	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
	Extreme fine structure	0.40	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	June 2017	SRL


Constructions with Troldekt installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
	Concrete 25 mm Troldekt											
	TCH 25 mm											
	Fine structure	0.10	0.15	0.30	0.65	0.95	0.85	0.35	0.55	D	April 2017	SRL
	Ultrafine structure	0.10	0.15	0.30	0.60	0.90	0.80	0.35	0.50	D	April 2017	SRL
	Extreme fine structure	0.10	0.15	0.30	0.60	0.90	0.70	0.35	0.50	D	April 2017	SRL
	Concrete 35 mm Troldekt											
	TCH 35 mm											
	Fine structure	0.10	0.25	0.45	0.85	0.85	0.90	0.50	0.60	D	June 2017	SRL
	Ultrafine structure	0.10	0.25	0.45	0.80	0.90	0.90	0.50	0.60	D	June 2017	SRL
	Extreme fine structure	0.10	0.25	0.50	0.85	0.90	0.90	0.50	0.60	D	June 2017	SRL

# Troldtekt Plus

## Installed on concrete


Constructions with Troldtekt Plus installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 25+20 mm Troldtekt Plus: - 25 mm Troldtekt - 20 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 45</p>												
	Fine structure	0.15	0.40	0.95	1.00	0.80	0.90	0.70	0.75	C	April 2024	SRL
	Ultrafine structure	0.15	0.45	1.00	1.00	0.80	1.00	0.75	0.85	C	April 2024	SRL
	Extreme fine structure	0.15	0.45	0.90	1.00	0.85	0.90	0.75	0.80	C	April 2024	SRL
 <p>Concrete 35+20 mm Troldtekt Plus: - 35 mm Troldtekt - 20 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 55 mm</p>												
	Fine structure	0.20	0.50	1.00	0.90	0.80	1.00	0.80	0.80	B	April 2024	SRL
	Ultrafine structure	0.20	0.55	1.00	0.95	0.85	0.95	0.85	0.85	B	April 2024	SRL
	Extreme fine structure	0.20	0.45	0.95	1.00	0.85	1.00	0.75	0.80	C	April 2024	SRL
 <p>Concrete 25+40 mm Troldtekt Plus: - 25 mm Troldtekt - 40 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 65 mm</p>												
	Fine structure	0.30	0.95	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2017	SRL
	Ultrafine structure	0.30	0.85	1.00	1.00	1.00	1.00	1.00	1.05	A	April 2017	SRL
	Extreme fine structure	0.25	0.85	1.00	1.00	1.00	1.00	1.00	1.05	A	April 2017	SRL

Constructions with Troldekt Plus installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute	
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class			
 <p>Concrete 35+40 mm Troldekt Plus: - 35 mm Troldekt - 40 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 75 mm</p>	Fine structure	0.30	0.90	1.00	0.95	0.95	1.00	1.00	1.00	A	June 2017	SRL	
	Ultrafine structure	0.30	0.90	1.00	1.00	0.95	1.00	1.00	1.00	A	June 2017	SRL	
	Extreme fine structure	0.35	0.90	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL

Construction with Troldekt Plus 25 installed on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete Troldekt Plus 25 with acoustic fleece</p> <p>TCH 55 mm</p>	Fine structure	0.10	0.30	0.70	1.00	0.95	0.95	0.60	0.75	C	Febr 2025	SRL
	Ultrafine structure	0.15	0.35	0.70	0.95	0.95	1.00	0.65	0.75	C	April 2024	SRL
	Extreme fine structure	0.15	0.30	0.65	0.90	0.95	1.00	0.60	0.70	C	April 2024	SRL


# Troldtekt design & Troldtekt design Plus

Installed on concrete

Constructions with Troldtekt design installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 35 mm Troldtekt Line TCH 35 mm</p>	Ultrafine structure	0.10	0.20	0.40	0.60	0.80	0.80	0.45	0.50	D	June 2018	SRL
	Concrete 40 mm mineral wool 70 kg/m <sup>3</sup> 35 mm Troldtekt Line TCH 75 mm	Ultrafine structure	0.30	0.85	1.00	1.00	0.95	1.00	1.00	1.05	A	June 2018






## Troldtekt A2

Installed on concrete






Construction with Troldtekt A2 installed directly on concrete		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 25 mm Troldtekt A2 TCH 25 mm</p>	Fine structure	0.05	0.10	0.25	0.45	0.75	0.60	0.30	0.40	D	June 2017	SRL
	Ultrafine structure	0.05	0.15	0.35	0.70	1.00	0.90	0.40	0.55	D	June 2017	SRL
	Extreme fine structure	0.10	0.15	0.35	0.60	0.90	0.75	0.40	0.50	D	June 2018	SRL





# Troldekt acoustic panels





Installed as suspended ceiling

Constructions with Troldekt		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 75 mm space 50 mm mineral wool 70 kg/m<sup>3</sup> 50 mm mineral wool 70 kg/m<sup>3</sup> 25 mm Troldekt TCH 200 mm</p>	Ultrafine structure	0.75	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2017	SRL
	 <p>Concrete 65 mm space 50 mm mineral wool 70 kg/m<sup>3</sup> 50 mm mineral wool 70 kg/m<sup>3</sup> 35 mm Troldekt TCH 200 mm</p>	Fine structure	0.70	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017
Ultrafine structure		0.75	1.00	1.00	1.00	1.00	1.00	1.00	1.10	A	June 2017	SRL
Extreme fine structure		0.70	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
 <p>Concrete 20 mm space 25 mm Troldekt TCH 45 mm</p>		Fine structure	0.15	0.25	0.40	0.75	0.70	0.80	0.45	0.55	D	Sept 2020
	Ultrafine structure	0.10	0.25	0.45	0.85	0.70	0.85	0.50	0.60	D	Sept 2020	SRL
	Extreme fine structure	0.15	0.25	0.50	0.85	0.80	0.85	0.50	0.60	D	Sept 2020	SRL
	 <p>Concrete 30 mm space 25 mm Troldekt TCH 55 mm</p>	Fine structure	0.10	0.20	0.55	0.90	0.70	0.95	0.50	0.60	D	April 2017
Ultrafine structure		0.10	0.20	0.50	0.85	0.70	0.90	0.50	0.55	D	April 2017	SRL
Extreme fine structure		0.10	0.20	0.50	0.85	0.70	0.85	0.50	0.55	D	April 2017	SRL
 <p>Concrete 100 mm space 25 mm Troldekt TCH 125 mm</p>		Fine structure	0.20	0.40	0.75	0.60	0.65	0.90	0.65	0.60	C	April 2017
	Ultrafine structure	0.20	0.35	0.70	0.65	0.65	0.90	0.65	0.60	C	April 2017	SRL
	Extreme fine structure	0.15	0.40	0.70	0.65	0.60	0.85	0.65	0.65	C	April 2017	SRL







Constructions with Trolldtekt		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 175 mm space 25 mm Trolldtekt</p> <p>TCH 200 mm</p>	Fine structure	0.25	0.50	0.60	0.50	0.70	0.90	0.60	0.60	C	Sept 2020	SRL
	Ultrafine structure	0.30	0.65	0.75	0.60	0.75	0.95	0.70	0.70	C	Sept 2020	SRL
	Extreme fine structure	0.30	0.65	0.75	0.60	0.80	0.95	0.70	0.70	C	Sept 2020	SRL
 <p>Concrete 30 mm space 35 mm Trolldtekt</p> <p>TCH 65 mm</p>	Fine structure	0.15	0.30	0.75	0.90	0.70	0.95	0.60	0.65	C	June 2017	SRL
	Ultrafine structure	0.15	0.30	0.70	0.90	0.75	0.95	0.60	0.65	C	June 2017	SRL
	Extreme fine structure	0.15	0.30	0.75	0.95	0.75	1.00	0.60	0.70	C	June 2017	SRL
 <p>60 mm space 35 mm Trolldtekt</p> <p>TCH 95 mm</p>	Ultrafine structure	0.15	0.35	0.85	0.75	0.85	0.95	0.65	0.70	C	June 2017	SRL
 <p>100 mm space 35 mm Trolldtekt</p> <p>TCH 135 mm</p>	Fine structure	0.15	0.35	0.80	0.65	0.75	1.00	0.65	0.65	C	June 2017	SRL
	Ultrafine structure	0.15	0.40	0.85	0.75	0.80	1.00	0.70	0.65	C	June 2017	SRL
	Extreme fine structure	0.15	0.40	0.85	0.80	0.80	1.00	0.70	0.70	C	June 2017	SRL
 <p>165 mm space 35 mm Trolldtekt</p> <p>TCH 200 mm</p>	Fine structure	0.25	0.70	0.70	0.60	0.85	1.00	0.70	0.70	C	June 2017	SRL
	Ultrafine structure	0.30	0.65	0.70	0.70	0.95	1.00	0.75	0.75	C	June 2017	SRL
	Extreme fine structure	0.25	0.70	0.80	0.65	0.85	1.00	0.75	0.75	C	June 2017	SRL




Constructions with Troldekt		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>145 mm space 30 mm mineral wool 70 kg/m<sup>3</sup> 25 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.45	1.00	1.00	1.00	0.85	1.00	0.95	1.00	A	April 2017	SRL
	Ultrafine structure	0.45	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2017	SRL
	Extreme fine structure	0.40	1.00	1.00	1.00	0.90	1.00	1.00	1.05	A	April 2017	SRL
 <p>130 mm space 45 mm mineral wool 30 kg/m<sup>3</sup> 25 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.50	1.00	1.00	0.95	0.80	1.00	0.90	1.00	A	April 2017	SRL
	Ultrafine structure	0.45	1.00	1.00	1.00	0.90	1.00	1.00	1.00	A	April 2017	SRL
	Extreme fine structure	0.45	1.00	1.00	1.00	0.85	1.00	0.95	1.05	A	April 2017	SRL
 <p>80 mm space 95 mm mineral wool 30 kg/m<sup>3</sup> 25 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.65	1.00	1.00	0.95	0.85	1.00	0.95	1.00	A	April 2017	SRL
	Ultrafine structure	0.60	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2017	SRL
	Extreme fine structure	0.65	1.00	1.00	1.00	0.90	1.00	1.00	1.05	A	April 2017	SRL
 <p>75 mm space 2x50 mm mineral wool 70 kg/m<sup>3</sup> 25 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.80	1.00	1.00	1.00	0.85	1.00	0.95	1.00	A	April 2017	SRL
	Ultrafine structure	0.75	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2017	SRL
	Extreme fine structure	0.80	1.00	1.00	1.00	0.90	1.00	1.00	1.05	A	April 2017	SRL

Constructions with Troldekt		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>135 mm space 30 mm mineral wool 70 kg/m<sup>3</sup> 35 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.40	1.00	1.00	1.00	1.00	1.00	1.00	1.10	A	June 2017	SRL
	Ultrafine structure	0.45	0.95	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
	Extreme fine structure	0.45	0.95	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
 <p>120 mm space 45 mm mineral wool 30 kg/m<sup>3</sup> 35 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.45	1.00	1.00	0.95	0.95	1.00	1.00	1.00	A	June 2017	SRL
	Ultrafine structure	0.50	1.00	1.00	1.00	1.00	1.00	1.00	1.00	A	June 2017	SRL
	Extreme fine structure	0.45	1.00	1.00	0.95	1.00	1.00	1.00	1.00	A	June 2017	SRL
 <p>70 mm space 95 mm mineral wool 30 kg/m<sup>3</sup> 35 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.70	1.00	1.00	0.95	1.00	1.00	1.00	1.00	A	June 2017	SRL
	Ultrafine structure	0.65	1.00	1.00	0.65	1.00	1.00	1.00	1.05	A	June 2017	SRL
	Extreme fine structure	0.65	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
 <p>70 mm space 65 mm space 2x50 mm mineral wool 70 kg/m<sup>3</sup> 35 mm Troldekt</p> <p>TCH 200 mm</p>	Fine structure	0.70	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL
	Ultrafine structure	0.75	1.00	1.00	1.00	1.00	1.00	1.00	1.10	A	June 2017	SRL
	Extreme fine structure	0.70	1.00	1.00	1.00	1.00	1.00	1.00	1.05	A	June 2017	SRL

# Troldtekt Plus

## Installed as suspended ceiling

Constructions with Troldtekt Plus		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 135 mm space 25+40 mm Troldtekt Plus: - 25 mm Troldtekt - 40 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 200 mm</p>												
	Fine structure	0.70	1.00	1.00	0.95	0.90	1.00	0.95	1.05	A	April 2024	SRL
	Ultrafine structure	0.70	1.00	1.00	0.95	0.95	1.00	1.00	1.05	A	April 2024	SRL
	Extreme fine structure	0.65	1.00	1.00	1.00	0.90	1.00	1.00	1.05	A	April 2024	SRL
 <p>Concrete 125 mm space 35+40 mm Troldtekt Plus: - 35 mm Troldtekt - 40 mm mineral wool 70 kg/m<sup>3</sup></p> <p>TCH 200 mm</p>												
	Fine structure	0.70	1.00	1.00	0.95	0.90	1.00	0.95	1.05	A	April 2024	SRL
	Ultrafine structure	0.70	1.00	1.00	0.95	0.95	1.00	1.00	1.05	A	April 2024	SRL
	Extreme fine structure	0.70	1.00	1.00	1.00	0.95	1.00	1.00	1.10	A	April 2024	SRL
 <p>Concrete 155 mm space 25+20 mm Troldtekt Plus: - 25 mm Troldtekt - 20 mm mineral wool 90 kg/m<sup>3</sup></p> <p>TCH 200 mm</p>												
	Fine structure	0.55	1.00	1.00	0.95	0.90	1.00	0.95	1.00	A	April 2024	SRL
	Ultrafine structure	0.60	1.00	1.00	0.95	0.90	1.00	0.95	1.00	A	April 2024	SRL
	Extreme fine structure	0.55	1.00	1.00	0.95	0.90	1.00	0.95	1.00	A	April 2024	SRL
 <p>Concrete 145 mm space 35+20 mm Troldtekt Plus: - 35 mm Troldtekt - 20 mm mineral wool 90 kg/m<sup>3</sup></p> <p>TCH 200 mm</p>												
	Fine structure	0.55	1.00	1.00	0.90	0.90	0.95	0.95	1.00	A	April 2024	SRL
	Ultrafine structure	0.65	1.00	1.00	0.90	0.90	1.00	0.95	1.00	A	April 2024	SRL
	Extreme fine structure	0.60	1.00	1.00	1.00	0.95	1.00	1.00	1.05	A	April 2024	SRL

Constructions with Troldekt Plus 15 - 25 - 35		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 185 mm space Troldekt Plus 15 with acoustic fleece TCH 200 mm</p>												
	Fine structure	0.50	0.85	1.00	0.80	0.90	0.95	0.90	0.85	A	Febr 2025	SRL
	Ultrafine structure	0.45	0.80	1.00	0.80	0.85	1.00	0.85	0.85	A	Febr 2025	SRL
	Extreme fine structure	-	-	-	-	-	-	-	-	-	-	-
 <p>Concrete 175 mm space Troldekt Plus 25 with acoustic fleece TCH 200 mm</p>												
	Fine structure	0.45	0.85	1.00	0.80	0.95	1.00	0.90	0.90	A	Febr 2025	SRL
	Ultrafine structure	0.50	0.85	1.00	0.85	1.00	1.00	0.95	0.95	A	Febr 2025	SRL
	Extreme fine structure	0.50	0.85	1.00	0.85	0.95	1.00	0.95	0.90	A	Febr 2025	SRL
 <p>Concrete 165 mm space Troldekt Plus 35 with acoustic fleece TCH 200 mm</p>												
	Fine structure	0.45	0.85	1.00	0.85	1.00	1.00	0.95	0.95	A	Febr 2025	SRL
	Ultrafine structure	0.45	0.90	1.00	0.90	1.00	1.00	1.00	0.95	A	Febr 2025	SRL
	Extreme fine structure	0.45	0.85	1.00	0.90	1.00	1.00	1.00	0.95	A	Febr 2025	SRL


# Troldtekt design & Troldtekt design Plus


Installed as suspended ceiling


Construction with Troldtekt v-line		Frequency [Hz]						Specifications			Date	Institute	
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class			
 <p>Concrete 175 mm space 25 mm Troldtekt</p> <p>TCH 200 mm</p>	Ultrafine structure	0.25	0.55	0.65	0.55	0.70	0.90	0,65	0,60	C	Febr 2025	SRL	
	Constructions with Troldtekt v-line Plus 25		Frequency [Hz]						Specifications			Date	Institute
 <p>Concrete 175 mm space Troldtekt v-line Plus 25 with acoustic fleece</p> <p>TCH 200 mm</p>		Ultrafine structure	0.50	0.85	1.00	0.85	0.95	1.00	0.95	0.90	A	Febr 2025	SRL
		Construction with Troldtekt line Plus 35		Frequency [Hz]						Specifications			Date
 <p>Concrete 165 mm space Troldtekt line Plus 35 with acoustic fleece</p> <p>TCH 200 mm</p>		Ultrafine structure	0.45	0.85	1.00	0.85	1.00	1.00	0.95	0.95	A	Febr 2025	SRL
		Construction with Troldtekt Tiles T24 Plus 25		Frequency [Hz]						Specifications			Date
 <p>Concrete 175 mm space Troldtekt Tiles T24 Plus 25 with acoustic fleece</p> <p>TCH 200 mm</p>		Ultrafine structure	0.45	0.80	1.00	0.80	0.85	1.00	0.85	0.85	A	-	Estimated


# Troldtekt A2

## Installed as suspended ceiling

Construction with Troldtekt A2		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 175 mm space 25 mm Troldtekt A2</p> <p>TCH 200 mm</p>	Fine structure	0.25	0.50	0.60	0.55	0.70	0.90	0.60	0.55	C	June 2018	SRL
	Ultrafine structure	0.25	0.50	0.65	0.55	0.70	0.90	0.65	0.60	C	June 2018	SRL

Construction with Troldtekt A2 Plus 15		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 185 mm space Troldtekt A2 Plus 15 with acoustic fleece</p> <p>TCH 200 mm</p>	Fine structure	0.45	0.80	1.00	0.80	0.90	1.00	0.90	0.90	A	Febr 2025	SRL
	Ultrafine structure	0.45	0.80	1.00	0.80	0.90	1.00	0.90	0.90	A	Febr 2025	SRL

Construction with Troldtekt A2 Plus 25		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 175 mm space Troldtekt A2 Plus 25 with acoustic fleece</p> <p>TCH 200 mm</p>	Fine structure	0.45	0.85	1.00	0.85	0.95	1.00	0.95	0.90	A	Febr 2025	SRL
	Ultrafine structure	0.50	0.85	1.00	0.85	1.00	1.00	0.95	0.90	A	Febr 2025	SRL
	Extreme fine structure	0.50	0.85	1.00	0.85	1.00	1.00	0.95	0.95	A	Febr 2025	SRL

Construction with Troldtekt A2 Plus 35		Frequency [Hz]						Specifications			Date	Institute
		125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
 <p>Concrete 165 mm space Troldtekt A2 Plus 35 with acoustic fleece</p> <p>TCH 200 mm</p>	Fine structure	0.45	0.85	1.00	0.85	1.00	1.00	0.95	0.90	A	Febr 2025	SRL
	Ultrafine structure	0.50	0.85	1.00	0.90	1.00	1.00	1.00	0.95	A	Febr 2025	SRL
	Extreme fine structure	0.50	0.85	1.00	0.90	1.00	1.00	1.00	0.95	A	Febr 2025	SRL

# Troldtekt baffles

Construction with Troldtekt baffles 30 mm		Frequency [Hz]						Specifications			Date	Institute
CC	Diagram	125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
		200 mm		0.30	0.35	0.40	0.60	0.75	0.90	0.50		
300 mm		0.20	0.30	0.35	0.50	0.65	0.80	0.45	0.45	D	March 2025	SRL
400 mm		0.15	0.25	0.30	0.45	0.60	0.70	0.40	0.40	D	March 2025	SRL

- Hanging height 50 mm
- Panel height 300 mm
- TCH 350 mm
- Ultrafine structure

Construction with Troldtekt baffles 30 mm		Frequency [Hz]						Specifications			Date	Institute
CC	Diagram	125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
		200 mm		0.25	0.30	0.40	0.55	0.75	0.90	0.50		
300 mm		0.20	0.25	0.35	0.45	0.65	0.80	0.45	0.40	D	March 2025	SRL
400 mm		0.20	0.20	0.25	0.45	0.60	0.70	0.35	0.35	D	March 2025	SRL

- Hanging height 200 mm
- Panel height 300 mm
- TCH 500 mm
- Ultrafine structure

Construction with Troldtekt baffles 30 mm		Frequency [Hz]						Specifications			Date	Institute
CC	Diagram	125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
		300 mm		0.30	0.35	0.50	0.65	0.75	0.90	0.55		
600 mm		0.20	0.25	0.35	0.45	0.50	0.65	0.45	0.40	D	March 2025	SRL
900 mm		0.10	0.15	0.25	0.35	0.35	0.50	0.35	0.25	D	March 2025	SRL

- Hanging height 50 mm
- Panel height 600 mm
- TCH 650 mm
- Ultrafine structure

Construction with Troldtekt baffles 30 mm		Frequency [Hz]						Specifications			Date	Institute
CC	Diagram	125	250	500	1000	2000	4000	$\alpha_w$	NRC	Class		
		300 mm		0.20	0.35	0.50	0.65	0.85	0.90	0.55		
600 mm		0.15	0.25	0.40	0.55	0.65	0.75	0.45	0.45	D	March 2025	SRL
900 mm		0.10	0.20	0.30	0.40	0.50	0.65	0.40	0.35	D	March 2025	SRL

- Hanging height 200 mm
- Panel height 600 mm
- TCH 800 mm
- Ultrafine structure



This document reflects Troldtekt's knowledge of certifications, standards, and products at the time of publication. No rights can be derived from this document. Changes, typesetting and printing errors reserved. The most recent version can be found online by scanning the QR code.

NOVEMBER 2025 EN V01

Troldtekt A/S  
 Sletvej 2 A  
 DK - 8310 Tranbjerg J  
 Tel +45 8747 8100  
 info@troldtekt.dk  
 www.troldtekt.com